

TECHNICAL DATA SHEET

Breathable Micro Mesh (lining)

Weight	80-130 g/m ² (2.4-3.8 oz/yd ²)
Composition	100% polyester or, for light stretch, ~90-95% PES / 5-10% elastane; mostly microfilament polyester.
Knit type	Breathable micro mesh (lining) · Mesh & Net
Use class	Sport
Stretch	Mechanical stretch
Knit	A fine, dense, small-holed knit (circular weft or warp/tricot based) with much smaller pores than sports net.
Hand	Very light, fine and soft; almost sheer, fluid drape, a dry hand that lies soft on the skin.
Typical use	Lining (jacket/swim/short liners) · light summer jerseys · sports innerwear
Strength	High airflow at very low weight — the go-to light lining and panel mesh.
Watch for	Being fine/light, durability and coverage as a standalone outer are limited; delicate to snags.

CERTIFICATIONS

ISO 9001	ISO 14001	ISO 45001	OEKO-TEX STEP	STANDARD 100	GRS · RCS
----------	-----------	-----------	---------------	--------------	-----------

Width, gauge, finishing options and test standards are shared on request.

Typical technical ranges

Weight tolerance	±5% (typical, dense/fine mesh); coarse open sports net and jacquard can run ±5–7% due to hole size/spacing and heat-set width-opening (very coarse builds may locally exceed ±7%)
Width	Open width typically ~150–190 cm; tubular ~30–100 cm. Spacer (double-bed) and jacquard on narrow machines usually sit near the low end. Exact width depends on machine diameter/needle count and finishing/heat-set set
Shrinkage (wash)	Up to ±3% after wash (with good heat-set usually ±1–3%); open/loose circular-knit net can reach ±4–5%, mainly lengthwise, with length/width difference being normal. PES has inherently low hygroscopic shrink; the main source is knit-tension relaxation, so it tracks heat-set quality
Color fastness	Wash 4–5, rubbing (dry) 4–5 / wet 3–4, light 4–6 (min grade). Disperse-dyed PES is generally good; deep/bright shades can sit near the low end for wet rub and perspiration
Abrasion / pilling	Typical Martindale ~15,000–40,000+ cycles; dense/fine builds (bird's-eye, jacquard, spacer) toward the top, coarse open net toward the bottom (on coarse open net, Martindale over the holes is of limited representativeness). Pilling typically 3–4 (filament PES sheds little fuzz). Main risk is snagging/laddering at large holes — not fuzzy pilling
Gauge / yarn	Typical machine gauge ~E18–E28 (coarse sports net E18–E22, fine lining/bird's-eye mesh E24–E28; spacer double-bed machines are a separate class). Yarn typically ~50–150 denier filament PES; fine microfilament lining mesh 50–75 den, structural/spacer heavier

These ranges are industry-TYPICAL / indicative values based on construction and fiber, not Fersan's binding QC measurements. Exact values are confirmed per order, approved sample and lot-based QC report.

Related reading: [Mesh and Piqué: Breathable Polyester Knits](#) · [Moisture-Wicking Finishing in Polyester Knits](#) · [Piqué, Bird's-Eye and Mesh: The Anatomy of Breathable Polyester Knits](#) · [The Physics of Moisture Transport: Capillarity and MMT](#)

